




**tangent**

ADVANCE COMPOSITES DIVISION

# **Glass Fabric**

**Technical Data**



Style	Finish	Fiber Type	Weave Pattern	Warp Yarn	Fill Yarn	Weight	Count - Ends x Picks (in)	Breaking Strength (lbs./inch)	Thickness (inch)	Density	LOI	Air Permeability (CFM/ft <sup>2</sup> & ½" WG)	Mullen Burst (lb. / in)
792	Untreated	Glass	Plain	ECD 900 1/0	ECD 900 1/0	0.68 (OSY)	66 X 38	25 X 10	0.0012	0	0	0 X 0	0
7781	Untreated	Glass	8 HS	ECDE 75 1/0	ECDE 75 1/0	8.95 (OSY)	58 X 54	350 X 340	0.009	0	0	0 X 0	0
76281	Untreated	Glass	4 HS	ECG 75 1/0	ECG 75 1/0	6 (OSY)	44 X 32	250 X 200	0.0068	0	0	0 X 0	0
7581	Untreated	Glass	8 HS	ECG 75 1/0	ECG 75 1/0	9.1 (OSY)	58 X 54	325 X 320	0.009	0	0	0 X 0	0
7576	Untreated	Glass	8 HS	ECG 75 1/0	ECG 150 1/0	10.6 (OSY)	120 X 24	650 X 100	0.0109	0	0	0 X 0	0
6781	Untreated	Glass	8 HS	SCG 75 1/0	SCG 75 1/0	8.95 (OSY)	58 X 54	350 X 300	0.009	0	0	0 X 0	0
6580	Untreated	Glass	8 HS	SCG 150 1/0	SCG 150 1/0	5.74 (OSY)	73 X 70	325 X 225	0.006	0	0	0 X 0	0
6581	Untreated	Glass	8 HS	SCG 150 1/2	SCG 150 1/2	8.95 (OSY)	58 X 54	350 X 250	0.009	0	0	0 X 0	0
6576	Untreated	Glass	8 HS	SCG 75 1/0	SCG 150 1/0	10.6 (OSY)	120 X 24	450 X 100	0.011	0	0	0 X 0	0
3788	Untreated	Glass	12 HS	ECG 37 1/4	ECG 37 1/4	51.8 (OSY)	42 X 35	1900 X 1350	0.05	0	0	0 X 0	0






Style	Finish	Fiber Type	Weave Pattern	Warp Yarn	Fill Yarn	Weight	Count - Ends x Picks (in)	Breaking Strength (lbs./inch)	Thickness (inch)	Density	LOI	Air Permeability (CFM/ft <sup>2</sup> & 1/2" WG)	Mullen Burst (lb. / in)
2500	Untreated	Glass	1 Pick Leno	ECH 25 1/0	ECG 75 2/3	8 (OSY)	16 X 8	150 X 250	0.016	0	0	0 X 0	0
2220	Untreated	Glass	4 HS	ECE 225 1/0	ECE 225 1/0	3.16 (OSY)	60 X 58	125 X 120	0.004	0	0	0 X 0	0
1584	Untreated	Glass	8 HS	ECG 150 4/2	ECG 150 4/2	26 (OSY)	44 X 35	950 X 800	0.026	0	0	0 X 0	0
1583	Untreated	Glass	8 HS	ECG 75 1/2	ECG 75 1/2	16.1 (OSY)	54 X 48	650 X 590	0.016	0	0	0 X 0	0
3784	Untreated	Glass	8 HS	ECG 37 1/2	ECG 37 1/2	25.4 (OSY)	42 X 35	950 X 800	0.026	0	0	0 X 0	0
1581	Untreated	Glass	8 HS	ECG 150 1/2	ECG 150 1/2	8.9 (OSY)	58 X 54	350 X 340	0.009	0	0	0 X 0	0
120	Untreated	Glass	4 HS	ECD 450 1/2	ECD 450 1/2	3.16 (OSY)	60 X 58	125 X 120	0.004	0	0	0 X 0	0
2510	Untreated	Glass	2x2 RH Twill	ECG 25 1/0	ECG 25 1/0	9.4 (OSY)	18 X 22	200 X 225	0.01	0	0	0 X 0	0



# tangent

**ADVANCE COMPOSITES DIVISION**

**CIN: U24290GJ2020PTC114057, GST No: 24AAHCT9020F1ZI**

-  Reg. Office: Plot No. 623, Phase-IV, G.I.D.C, Vatva, Ahmedabad-GJ-382445,INDIA.
-  +91 79 4005 1143, +91 79 2589 3255
-  +91 99989 57557
-  [info@tangentscience.com](mailto:info@tangentscience.com)
-  [www.tangentscience.com](http://www.tangentscience.com)

